IN THE SPECIFICATION

Please replace paragraph 122 on page 29, with the following amended paragraph.

The wet pulverization was performed by filling zirconia balls having a diameter of 10 mm in a ball mill pot by 30 % by volume of the ball mill pot capacity and a oxide slurry including a solid content of 25 % ~~by 20 5~~ by volume thereof.

Please replace Table 1-1, spanning pages 41-42, with the following amended Table.

Table 1-1

| | Carrier | | | | | |
	Carrier magneti-zation σb (emu/g)	Desorbed carrier magneti-zation σa (emu/g)	$\sigma a/\sigma b$ ~~$\Sigma a/\sigma b$~~	Weight-average particle diameter (D4) (µm)	Number-average particle diameter (D1) (µm)	D4/D1
Ex. 1	65	63	0.97	36.5	34.3	1.1
Ex. 2	70	65	0.93	35.8	30.5	1.2
Ex. 3	52	51	0.98	36.4	33.0	1.1
Ex. 4	69	66	0.96	34.7	33.9	1.0
Ex. 5	54	52	0.96	37.2	35.3	1.1
Ex. 6	65	62	0.95	39.4	30.7	1.3
Ex. 7	65	63	0.97	36.5	34.3	1.1
Ex. 8	65	63	0.97	36.5	34.3	1.1
Ex. 9	65	62	0.95	36.7	35.1	1.0
Ex. 10	65	63	0.97	35.9	34.4	1.0
Ex. 11	65	63	0.97	36.5	34.3	1.1
Ex. 12	65	63	0.97	36.5	34.3	1.1
Ex. 13	65	63	0.97	36.5	34.3	1.1
Ex. 14	65	63	0.97	36.5	34.3	1.1
Ex. 15	70	65	0.93	35.8	30.5	1.2
Ex. 16	65	63	0.97	36.5	34.3	1.1
Ex. 17	54	52	0.96	37.2	35.3	1.1
Ex. 18	65	63	0.97	36.5	34.3	1.1
Ex. 19	65	63	0.97	36.5	34.3	1.1
Ex. 20	65	63	0.97	36.5	34.3	1.1
Com. Ex. 1	65	54	0.83	36.7	35.1	1.0
Com. Ex. 2	78	76	0.97	37.3	33.5	1.1
Com. Ex. 3	50	49	0.98	34.9	32.1	1.1

Com. Ex. 4	73	70	0.96	39.6	37.9	1.0
Com. Ex. 5	44	42	0.95	36.2	33.9	1.1
Com. Ex. 6	65	64	0.98	24.8	24.5	1.0
Com. Ex. 7	65	63	0.97	67.0	62.4	1.1
Com. Ex. 8	65	61	0.94	34.2	32.5	1.1
Com. Ex. 9	65	62	0.95	38.4	27.9	1.4
Com. Ex. 10	65	63	0.97	36.5	34.3	1.1
Com. Ex. 11	65	63	0.97	36.5	34.3	1.1